



DX 660 nbr

Style DX 660 is a high quality general service sheet, manufactured with synthetic fibers and an NBR binder. Recommended for use in sealing against oils, solvents, fuels, non-aggressive solutions, and service conditions up to 750°F. Available in thicknesses from 1/64" through 1/4"

- **Synthetic fiber**
- **59" x 63" and 59" x 126"**
- **Great general service material**

DX 660 Physical Properties

Color	Green
Density (lbs/cubic ft)	109 lbs/ft ³
Maximum Service Temperature	750°F / 398°C
Recommended Maximum Continuous Temperature*	460°F / 237°C
Maximum Service Pressure*	1380 psi
Compressibility (after 1 hour at 210° F) - ASTM F36A	7-17%
Recovery ASTM F36A	45% minimum
Creep Relaxation ASTM F38B	25% max
Thickness Increase (max%) ASTM F146 (ASTM Oil #3)	12% max
Weight Increase (max%) ASTM F146 (ASTM Oil Fuel B)	15% max
Thickness Increase (max%) ASTM F146 (ASTM Oil Fuel B)	12% max
ASTM F104 Line Call out	F712120E22M5

DX 660 P x T = 350,000 (for 1/16")

P x T, or pressure times temperature, is used to help determine the suitability of a gasket material in a given application. Using only temperature or pressure figures can be misleading. Maximum temperature and pressure represent maximum values and should not be used simultaneously. They should be used only as guidance, since other variables, such as installation procedures and loading values also determine performance. Use the chart at the right to check the suitability of DX 660 in your application by considering the combination of pressure and temperature.

-  **Desired Range:** If P x T falls within this area, it is recommended for use.
-  **Consult Engineering:** If the P x T falls within this area, please consult engineering.
-  **Not Recommended:** If the P x T falls within this area, it is not recommended for use.

